



Cleaning and Sterilization Instructions



8400 Green Meadows Dr. N.
P.O. Box 545
Lewis Center, OH 43035 USA
USA: 800.964.8324
P: 740.548.4100 F: 740.548.7617

Abrasive Technology Ltd. EC REP
Unit 11 Boundary Business Court
92-94 Church Road
Mitcham, Surrey CR4 3TD
P: +44.20.7471.0200
F: +44.20.7471.0202

Manufacturer: Abrasive Technology, Inc.	
Devices: Two Striper® Diamond Dental Finishing Strips & Compo-Discs®	
WARNINGS	<p>General</p> <ol style="list-style-type: none"> Thoroughly dry the devices after all steps, if they will sit for more than 15 minutes prior to the next step. All solutions used must be compatible with stainless steel (alkaline, acidic, or aldehyde solutions may cause damage). Follow all applicable solution or equipment manufacturer's instructions. All applicable solutions and equipment should meet national regulatory requirements. <i>These devices are NOT supplied sterile.</i> Clean and sterilize prior to use, as follows.
Processing limitations	None, other than diamond wear, to be determined by the user

INSTRUCTIONS	
Initial treatment at the point of use	Reprocess the devices as soon as possible after use. Do not allow embedded material to dry. Keep the devices immersed in solution from the time they are used until they are cleaned – use enzymatic cleaner, cleaning/disinfecting, cleaning, or water (in order of preference).
Preparation before cleaning	Not applicable
Cleaning: Automated	<ol style="list-style-type: none"> Rinse the devices under cold, heavy running tap water. Ultrasonically clean the devices in enzymatic cleaner (Premier Brite Shield™ Enzymatic Static Soak and Ultrasonic Cleaner, or equivalent, dissolved in tap water) for at least five minutes. Avoid the devices in contact with each other during cleaning (do not pile). Rinse thoroughly with tap water.
Cleaning: Manual	Not applicable
Disinfection	Not applicable
Drying	Dry by wiping with absorbent, disposable wipes, dry heat, or filtered, pressurized air. Devices that are not completely dry may corrode.
Maintenance, Inspection and Testing	Visually examine the devices for contamination. Magnification is recommended. <i>Repeat the above steps for any devices that are still contaminated.</i>
Packaging	Sterilization pouch
Sterilization	Steam sterilize, pre-vacuum, average pressure of 30psi (207 kPa), minimum of 4 minutes, 132°C, and a minimum dry time of 22 minutes.
Storage	Store the devices in the sterilized wrap.
Additional Information	Some surface discoloration or dulling may routinely occur after moist heat sterilization. This does not affect performance.
Manufacturer Contact	740-548-4100

The instructions provided above have been validated by the manufacturer of the medical device as being capable of preparing a medical device for use/reuse. It remains the responsibility of the processor to ensure that the processing, as actually performed using equipment, materials and personnel in the processing facility, achieves the desired result. This requires verification and/or validation and routine monitoring of the process. **Date issued: 11/2017**